



# Elasto-Deck 5000HT Light Duty (Vehicular/Pedestrian) System

31 Mils DFT

**BROADCAST AND BACK ROLL COAT:  
ELASTO-GLAZE 6001ALHT**

4

- 110 Sq ft per gallon (11 Mils DFT)
- Broadcast aggregate 15-18 per 100 Sq ft Uniformly (Not to refusal) and back roll

**BASE COAT:  
ELASTO-DECK 5001HT**

3

- 60 Sq ft per gallon (20 Mils DFT)

**PRIMER COAT:  
ELASTO-POXY PRIMER VOC OR W.B.**

2

- 225-250 Sq ft per gallon (4 Mils DFT)

**CONCRETE SUBSTRATE**

1

(Prep surface, detail cracks, penetrations and flashing)

