

DESCRIPTION

PolySpec[®] Moisture Mitigating Primer is a low viscosity, 100% solids, high build, epoxy primer designed for use under TuffRez[®] Coating systems or where a high build primer is needed. This primer enhances adhesion by penetrating into the concrete substrate and helps reduce bubbling and pinholes that may occur when coating porous surfaces with high build coatings. PolySpec[®] Moisture Mitigating Primer meets OSHA, State VOC regulations and USDA standards for maintenance protective coatings not in direct contact with food in federally inspected meat and poultry plants.

TYPICAL APPLICATION

• Primer	PolySpec [®] MMP Primer @ 12-16 Milis
• Overcoat	Flooring or Lining System from PolySpec [®]

PERFORMANCE DATA

VOC03 lb/gal; 3.7 gm/L
Volume Solids 100%
Viscosity 800-1000 cps at 72°F
Service Temperature 180°F Dry Heat Resistance

STORAGE & INSTALLATION

Storage EnvironmentDry area, 50–90°F
Application Temperature, ambient 55–95°F
Relative Humidity 85% Maximum
Flash Point200°F
Shelf Life 18 Months
Pot Life, @ 72°F35 Minutes
Set Time, @72°F Minimum: 8 Hours, Maximum: 72 Hours
Recoat Window Minimum: 6 Hours, Maximum: 48 Hours

Material cures more slowly at cooler temperatures, and working time will be substantially reduced at higher temperatures. In hot weather, material should be cooled to 65°F to 80°F prior to mixing and application to improve workability and avoid shortened pot life. The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown above may result.

CONSIDERATIONS & LIMITATIONS

1. PolySpec[®] does not recommend that grit be broadcast or otherwise introduced into PolySpec[®] MMP Primer. If enhanced slip resistance is desired, a flooring system topcoat may be specified to serve this function
2. Do not thin with solvents unless advised to do so by PolySpec[®].
3. Confirm product performance in specific chemical environment prior to use.
4. Prepare substrate according to “Surface Preparation” portion of this document.
5. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab.
6. Always use protective clothing, gloves and goggles consistent with OSHA regulations during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Material Safety Data Sheet for detailed safety precautions.
7. For industrial/commercial use. Installation by trained personnel only.

PolySpec[®] MMP Primer

TECHNICAL DATA SHEET

High Build Epoxy Primer for Concrete

BENEFITS

- 100% Solids formulation eliminates solvent odors
- Low viscosity formulation penetrates and seals concrete pores.
- Covers rough surfaces to provide superior seal and adhesion

RECOMMENDED USES

- To be used for open and porous substrates
- Penetrate and seal for scarified, shot blasted, or sandblasted concrete.

GENERIC DESCRIPTION

Primer

STANDARD COLOR

Transparent Amber

PACKAGING

1-Gallon Unit
5-Gallon Unit

COVERAGE

114 ft²/ gallon @ 14 mils

SURFACE PREPARATION

New Concrete: All surfaces must be firm, clean, dry and well cured before coating. Newly poured concrete must age at least 30 days at temperatures over 70°F before coating. Form release agents, curing compounds, salts, hardeners and other foreign matter will interfere with adhesion and must be removed by sandblasting, shot blasting, mechanical scarification or suitable chemical means. If a curing membrane was not used, then proceed with a 16% muriatic acid etch (1 gal. 32% muriatic acid to 1 gal. water) at a rate of 75 sq. ft./gal.

Old Concrete: Coating older, uncoated concrete floors is done in much the same manner as new concrete. Before etching, the concrete surface must be thoroughly cleaned with a strong detergent cleaner to remove all grease, oils, etc. All loose concrete must be removed. Form release agents, hardeners, etc., must be removed using same procedure as for new concrete. Holes and cracks should be filled. If surface deterioration presents an unacceptably rough floor, the floor should be resurfaced and patched.

Wood: A clean, sound wood surface is required. Remove any oils and dirt from the surface using degreasing solvent or strong detergent. Follow with sanding to remove loose or deteriorated surface wood.

Refer to PolySpec® Surface Preparation Guidelines for more details.

INSTALLATION STEPS

1. Before mixing PolySpec® Moisture Mitigating Primer it is important that the surface is completely prepared and ready and that all tools and equipment are handy.
2. To mix 1 gallon units: Use electric or air mixer (approximately 250 rpm) with metal mixing blade (Jiffy Model HS or equal). Pour hardener contents into slack-filled resin can and mix for 2 to 3 minutes until material is thoroughly blended.
3. To mix 5 gallon units: Use same procedure as 1 gallon units except a larger blade (Jiffy Model ES or equal) is required.
4. Immediately pour a substantial portion of mixture onto the floor and spread material using a flat, rubber squeegee using sufficient pressure to work the primer into the porous surface.
5. Immediately back roll the material with a quality 3/8" nap roller leaving 12 to 16 mils on the surface.
6. The fast set primer can be top-coated in 9 hours at 72°F. The primer must be tack free before top coating. If pinholes or porosities are evident after initial cure of the primer, re-priming may be necessary; especially on very porous concrete.
7. For best results, clean tools and equipment with PolySpec® All Purpose Cleaner, a nonflammable and non-evaporating cleaner. Always wear gloves when using this product.

1R: .52H / DOC PSMMP TDS

PolySpec is a ® Registered Trademark of PolySpec L.P.

Thiokol is a ® Registered Trademark of Toray Fine Chemicals Co., Ltd.

Rev 01/12

© Copyright 2005 PolySpec L.P. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your PolySpec representative for current technical data and instructions.

PolySpec, L.P. warrants its products to be free from defects in material and workmanship. PolySpec's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at PolySpec's option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to PolySpec in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify PolySpec of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

PolySpec makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall PolySpec be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by PolySpec, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. PolySpec cannot guarantee that color will conform to sample, if provided.