




Elasto-Deck BT H2O (Waterproofing - Concrete)

Over occupied areas - 60 Mils DFT




SECOND COAT: 42 Sq ft per Gallon (30 Mils DFT)
 • Elasto-Deck BT H2O

FIRST COAT: 42 Sq ft per Gallon (30 Mils DFT)
 • Elasto-Deck BT H2O

PRIMER COAT: 225-250 Sq ft per Gallon (4 Mils DFT)
 • Elasto-Poxy Primer VOC or Deck-Thane Primer

DETAIL WORK: Concrete Substrate
 1. V-Groove and caulk cracks, fill voids rock pockets with Permthane SM7108 and trowel flush
DETAIL WORK: Vertical to Horizontal transitions, Inside Corners Joints, Drains etc.
 1. Contact manufacture for how to address these specific conditions





Elasto-Deck BT H2O (Waterproofing - Concrete)

Suggested Tools & Sundries



- Acetone/Xylene
- Blue Tape/Masking Tape
- Plastic Sheeting Roll
- Caulking gun
- Pool Trowel
- 1/8" Notched Trowel
- 1/8" Notched Squeegee w/ Handle
- Rubber Gloves
- Electric Drill
- Jiffy Mixing Paddle
- Screw Driver/Lid Opener
- Rags
- Chip Brush
- Push Broom
- Roller Handle with pole
- Roller Covers 3/4"-1"
- Empty Pail (Broadcast aggregate)
- Trash Bags
- Scissors