



SUPERCURE AL

COLD WEATHER ACCELERATOR

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION:

Pacific Polymers® SUPERCURE AL is a cold weather accelerator for **ELASTO-GLAZE 6001AL-HT**, a polyurethane based sealer manufactured by **ITW POLYMERS SEALANTS NORTH AMERICA, INC.** It helps to accelerate tack free time and cure time.

BASIC USES:

SUPERCURE AL is designed to be used as an accelerator for:

- **ELASTO-GLAZE 6001AL-HT**

LIMITATIONS:

- **Not for sale in SCAQMD**
- Do not add the accelerator in excess of what is required. Adding the accelerator will reduce the work life of the product. **SUPERCURE AL** is moisture sensitive. Do not leave open container exposed to moisture or direct sunlight.

SHELF LIFE: 1 year @ 77°F (25°C) when stored in dry cool location.

COLOR: Clear to light Yellow

SIZE: Quarts only.

WARNING AND HAZARDS:

- Before using the products, always refer to SDS for important warnings and safety information. Use only in areas with adequate ventilation. Avoid breathing vapors. Keep away from heat and flame. Avoid contact with eyes and skin. In the event of skin contact, remove immediately and wash with warm, soapy water. Wear suitable eye protection. Always wash hands before eating.

TECHNICAL: (See below)

MIXING INSTRUCTION

- Add up to 1-quart **SUPERCURE AL** to a 5-gallon pail of **Elasto-Glaze 6001AL-HT**.
- **Do not add more than one QUART per pail.**
- Mix immediately. (To avoid gelation and skinning) Mixing is best achieved with a slow speed, heavy-duty drill (250 - 400 RPM) for two to three minutes, using a Jiffy mixing paddle.
- Apply the mixed material immediately using a 1/4"-3/8" nap paint roller), spray and/or a brush.
- Use a thin nap roller to avoid thick applications.
- Caution! Improper mixing can leave stained spots on the surface of the top coat. Once catalyst is added in the 5-gallon container, it will start to react.

CLEAN UP:

Equipment and tools should be cleaned immediately after use with acetone or other exempt solvent.

AVAILABILITY AND COST:

SUPERCURE AL is supplied through building material dealers. These products are designed and manufactured to be installed by professional installers familiar with surface preparation and application procedures. All others should consult a professional installer; those who choose to install these products without professional assistance do so at their own risk.

TECHNICAL SERVICE

All of the latest updates to product data and specifications are available at www.pacpoly.com. Since product data and specifications change, it is the user's responsibility to make certain the most current versions of product data and specifications are being used.

Technical assistance can be obtained by contacting:

ITW POLYMER SEALANTS NORTH AMERICA
12271 Monarch Street
Garden Grove, CA 92841
Tel: 1-800-888-8340
Fax: 714-898-5687

PRODUCT WARRANTY:

SATISFACTORY RESULTS DEPEND NOT ONLY UPON QUALITY PRODUCTS BUT ALSO UPON FACTORS BEYOND OUR CONTROL; METHODS OF APPLICATION AND SITE CONDITIONS ARE EXAMPLES OF SUCH FACTORS AND CAN AFFECT PRODUCT PERFORMANCE. THIS WARRANTY CONSEQUENTLY EXTENDS ONLY TO PRODUCTS INSTALLED IN STRICT ACCORDANCE WITH THE MANUFACTURER'S SPECIFICATIONS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF, BY HIS OWN INFORMATION AND TESTS, OF THE SUITABILITY OF THE PRODUCT FOR HIS OWN INTENDED USE; USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM HIS USE OF THE PRODUCT. THE SUBSTRATE TO WHICH THE PRODUCT IS APPLIED MUST BE SOUND STRUCTURALLY AND OTHERWISE. STRUCTURAL OR SUBSTRATE FAILURES OR IMPERFECTIONS RESULTING IN DAMAGE TO OR FAILURE OF THE PRODUCT ARE NOT COVERED BY THIS WARRANTY.

SINCE THE USE OF THE PRODUCT IS BEYOND THE CONTROL OF THE MANUFACTURER, THE MANUFACTURER ASSUMES NO LIABILITY FOR MISAPPLICATION AND MISUSE OF THE PRODUCT.

THIS WARRANTY DOES NOT COVER CONSEQUENTIAL DAMAGES, NOR DOES IT COVER THE LABOR ATTENDANT TO REPLACING PRODUCT IN THE EVENT OF A PRODUCT FAILURE. THE WARRANTY ONLY EXTENDS TO REPLACEMENT OF THE PRODUCT ITSELF.

ALL PRODUCTS PROVEN TO BE DEFECTIVE IN MANUFACTURE WILL BE REPLACED AT NO CHARGE. SINCE THE USE OF THESE PRODUCTS IS BEYOND OUR CONTROL WE CANNOT ASSUME ANY RISK OR LIABILITY FOR RESULTS OBTAINED, NOR CAN WE ACCEPT DAMAGES IN EXCESS OF THE PURCHASE PRICE OF THESE PRODUCTS.

Complete technical information is available from
ITW Polymers Sealants North America, Inc.

(POTLIFE/TACK FREE/LIGHT TRAFFIC)

Product	AT 40°F	AT 60°F	AT 70°F
ELASTO-GLAZE 6001AL-HT	1-2 hrs/8 hrs/16-24 hrs	1-2 hrs/4-6 hrs/10-12 hrs	1-2 hrs/2 hrs/4 hrs